

## Key Features

- Very clear and UV resistant
- Expels trapped air
- Fast curing
- Tough and hard wearing
- Excellent mechanical properties

## Product Description

XCR™ is an extreme performance, high clarity epoxy developed for demanding visual applications including carbon fibre skinning, board manufacture and wood finishing. XCR™ is intended for use where laminates will remain unpainted, showcasing reinforcements like carbon fibre or natural fibres, inlaid graphics or beautiful wood grains.

To ensure the perfect finish, XCR™ uses special technology to enhance fibre wet-out and expel trapped air. Its fast cure allows multiple layers to be built-up in minimum time, significantly speeding up 'skinning' processes requiring multiple coats.

XCR™ will cure to a hard, durable, UV resistant finish which can be flatted and polished to a high gloss or over-painted with a suitable clear coat/lacquer. The resin offers excellent cured mechanical properties making it suitable for use laminating or finishing sports/recreational equipment like skis, boards or boat decking.

XCR™'s distinctive 'purple' colour is due to the advanced UV protection agents used in the resin. Once mixed with its hardener this colour diminishes and when used as directed as a thin coating, the tint is barely detectable and in fact enhances the appearance of fibres (such as carbon fibre) and inlaid graphics. Once cured, XCR™ needs to be flatted using abrasive paper and then polished using a cutting/polishing compound to achieve a high gloss finish.

XCR™ is NOT intended as a coating resin for artwork. For particularly colour-sensitive projects requiring a self-levelling 'pour and leave' finish like this, specialist ArtResin® should be used.

## Recommended Uses

- Carbon fibre 'skinning'
- Wood coating / deck finishing
- Surfboard/sailcraft building
- R/C aircraft wing skinning
- Ski/snowboard finishing

## Mechanical Properties

Cured Resin Properties

	Units	Post Cured
Tg Onset (DMTA)	°C	80.0
Tg Max(DMTA)	°C	80.0
Maximum Tensile Strength	MPa	68.0
Tensile Breaking Strength	MPa	65.0
Tensile Modulus	GPa	3.40
Maximum Flexural Strength	MPa	117.0
Flexural Breaking Strength	MPa	103.0
Flexural Modulus	GPa	3.20
Compressive Yield Strength	MPa	103.0
Offset Compression Yield	%	14.3
Elongation at Max Strength	%	5.6
Elongation at Break	%	8.5
ILSS	MPa	48.0

## Process Specific Information

### Carbon Fibre Skinning

Overlaying carbon fibre or decorative reinforcements over existing parts like interior trim or even exterior vehicle panels is a skilled but much in-demand process. XCR™ addresses the long-standing challenges of air entrapment, clarity, UV stability and cure time between stages head-on with a unique combination of properties designed to deliver stunning, reliable results in the shortest possible time.

### Overlaminating with Other Materials

In the same way that XCR can be used to apply a glossy, hard wearing 'skin' of carbon fibre to any part, it can also be used to apply a durable, glossy layer of almost any fabric or material to a wide range of objects including furniture, interior trim or even music instruments. Materials including natural fibres (coconut mat, coffee sacks, flax), fabrics (denim, printed fabrics) and technical materials can all be used to create stunning, unique surfaces to a wide range of objects.

### Board Building and General Laminating

Not only does XCR™ provide a clear, vibrant finish to a range of reinforcements and substrates, it also has excellent mechanical properties comparable to most structural laminating epoxies and so can be used as a clear, UV stable laminating resin in conjunction with reinforcements like carbon fibre, glass fibre and natural reinforcements like flax and jute.

Its hard-wearing, fast curing properties make XCR™ ideal for a range of 'hot-coating' processes such as laminating EPS cores for surfboard manufacture. XCR™ is entirely solvent and styrene free and will not attack or affect EPS foam. Once fully cured, XCR™'s advanced mechanical properties offer excellent strength and damage tolerance.

The clarity and UV stability of the resin further enhance inlaid graphics or the natural appearance of the reinforcements used. When used in conjunction with

appropriate grades of glass reinforcement, XCR™ can produce a laminate of excellent clarity.

## Coating Wood

XCR™ has outstanding properties when used to preserve, protect, strengthen and enhance wooden surfaces. When applied to wood surfaces such as boat decking, traditional skis and boards or furniture, XCR™ can be used to create a hard-wearing protective layer which can be flatted and polished to a deep, glossy finish.

## Hardener Crystallisation

The Hardener is sensitive to low temperatures and if the hardener gets cold (either in storage or transport), it can crystallise; this does not damage the hardener at all and can be reversed by warming the hardener in its container with the lid securely in place. The longer it has been crystallised, the longer it will take to reverse. This can be achieved by sitting it directly onto a radiator, putting it into an oven on a low setting or standing the container in hot water. We recommend mixing the resin at around 20°C to prevent it crystallising while being mixed or used.

## Instructions for Use

XCR™ is a chemical product for professional use. It is essential to read and understand the safety and technical information before use.

Follow the guidelines for safe use outlined in the SDS which include the use of appropriate hand and eye protection during mixing and use.

## Mix Ratio

### Mix Ratio 100:41 by Weight

XCR™ Epoxy Coating Resin should be mixed with XCR Epoxy Coating Hardener at a ratio of 100 parts of resin to 41 parts of hardener, by weight.

### Mix Ratio 2:1 by Volume

If you would prefer to mix by volume then the mix ratio should be adjusted to 2 parts resin to 1 part hardener, by volume.

When working with any epoxy resin, it is essential to mix the resin and hardener exactly at the correct mix ratio. Failure to do so will result in a poor or only partial cure of the resin, greatly reduced mechanical properties and possibly other adverse effects. Under no circumstances add 'extra hardener' in an attempt to speed up the cure time; epoxies do not work in this way.

## Mixing Instructions

XCR™ is a highly reactive (fast curing) resin system. Only weigh out and mix as much resin as you can use within the pot life.

Weigh or measure the exact correct ratio of resin and hardener into a straight sided container. Using a suitable mixing stick begin to mix the resin and hardener together to combine them completely.

Spend at least one minute mixing the resin and hardener together, paying particular attention to the sides and base of the container. Remember: Any resin that has not been thoroughly combined with hardener will not cure.

Once you have finished mixing in one container, it is good practice to transfer the mixed resin into a second container and undertake further mixing of the resin using a new mixing stick. Doing so will eliminate the risk of accidentally using unmixed resin from the bottom or sides of the container.

## Pot-Life / Working Time / Cure Time

XCR™ is a highly reactive resin system and once the resin has been mixed with the hardener, the reaction will start to give off heat (exotherm) which will further accelerate the cure of the resin, especially when the resin is in the mixing pot. Transfer the resin from the mixing pot onto the part as soon as possible to extend the working time and avoid the risk of uncontrollable rapid cure in the mixing pot.

As with all epoxies, the pot-life/working time will vary significantly depending on the ambient temperature, the starting temperature of the resin and hardener and the amount of resin mixed.

XCR can be used in ambient temperatures between 15°C (59°F) and 30°C (86°F). For best results, an ambient temperature of at least 20°C (68°F) is recommended. Ensure that both resin and hardener containers are within this temperature range before use.

The table below gives an indication of pot-life and cure properties at a range of different ambient temperatures.

	Mixed Resin and Hardener	
	20°C (68°F)	30°C (86°F)
Pot-Life - 150g Mixed	8mins	4mins
Overcoat Time	2:51	1:42
Initial Cure*	8:33	5:06

Time shown in Hrs:mins

## Overcoating (Building Up Layers)

When using XCR™ for carbon fibre 'skinning' or to build up a thick coat of resin over any part or material it is recommended that subsequent layers of resin are applied once the previous application has firmed up but before it reaches its 'tack-free' stage. Applying additional layers at this 'overcoat time' (or 'B stage') means that they can be applied without any surface preparation and that they will bond chemically to the still tacky layer underneath.

The table above indicates the approximate 'overcoat time' when a new layer of resin should be applied over the previous layer although you should check the status of the cure beforehand. If the resin feels firm but still tacky, this is the right time to overcoat.

If the resin exceeds the 'overcoat time' and reaches its 'tack-free' point then it cannot be over-coated without first allowing it to cure for at least 9hrs (at 20°C) and then keying the surface with an abrasive paper to facilitate a mechanical bond between the original and new resin layers.

See notes below for important advice relating to post-curing of 'skinned' parts.

## Full Cure / Post-Cure

As with most epoxy systems, where parts cure in normal ambient temperatures, full cure is not reached for several days. Although parts will be handleable after around 9hrs (at 20°C), full mechanical properties will take at least 14 days to develop in (at 20°C). Where possible, avoid exposing the cured resin to full service rigours for at least this time.

To achieve full mechanical properties, a higher heat deflection temperature and a harder, more colour-stable laminate, an elevated temperature post-cure is highly recommended. During post-cure, the resin will initially soften before it hardens further and so it is recommended to leave moulded parts in their mould during post cure to ensure that they are fully supported. Skinned or over-laminated parts will not require supporting during post-cure.

Having allowed the laminate to cure fully at room temperature for at least 24hrs, post cure for 6hrs at 70°C (or longer at lower temperatures) to achieve full properties.

## Post-Curing Skinned or Over-laminated Parts

When following the 'skinning' process of over-laminating parts with carbon fibre or other reinforcements, it is **STRONGLY** recommended to post-cure parts **BEFORE** flattening and polishing them as post-curing will cause some sinking of the resin surface.

Once post-cured, this fully cured surface can be flattened and polished for a perfect durable finish.

## Transport and Storage

Resin and hardener should be kept in tightly sealed containers during transport and storage. Both the resin and hardener should be stored in ambient conditions of between 20°C (68°F) and 25°C (77°F).

When stored correctly, the resin and hardener will have a shelf-life of 12 months. Although it may be possible to use the resin after a longer period, a deterioration in the performance of the resin will occur, especially in relation to clarity and cure profile.

Pay particular attention to ensuring that containers are kept tightly sealed. Epoxy hardeners especially will deteriorate quickly when exposed to air.

## Disclaimer

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

Our technical advice, whether verbal or in writing, is given in good faith but Easy Composites Ltd gives no warranty, express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product for their particular application and circumstances.

Easy Composites Ltd shall be in no way responsible for the proper use and service of the product, nor for the safeguarding of personnel or property, all of which is the duty of the user. Any information or suggestions are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights. Before using any of our products, users should familiarise themselves with the relevant technical and safety datasheets provided by Easy Composites Ltd.

**[XCR]** is a trademark of Easy Composites Ltd.

### Easy Composites Ltd

Unit 39, Park Hall Business Village,  
Stoke on Trent, Staffordshire, ST3 5XA  
United Kingdom.  
Tel. +44 (0)1782 454499  
Email [sales@easycomposites.co.uk](mailto:sales@easycomposites.co.uk)  
Web [www.easycomposites.co.uk](http://www.easycomposites.co.uk)

### Easy Composites EU B.V. (EU Customers)

Beneluxbaan 16,  
Rijen, 5121 DC  
Netherlands  
Web [www.easycomposites.eu](http://www.easycomposites.eu)

